

Codice: MMO

## Smalto Motori Marini

### FAST DRYING, GLOSS ONE COMPONENT MARINE MOTORS PAINT



It is a fast drying enamel providing a gloss finish, withstanding service temperatures of marine engines, oils, diesel and salt water. Available in the most common colours of marine engines.

#### Technical Characteristics

<b>Paint Type</b>	One component
<b>Binder type A</b>	Chlorinated-alkyd
<b>Specific gravity kg/lit (±0,05)</b>	1.100-1.300 secondo il colore
<b>Solids content (volume) ±2</b>	50%
<b>Viscosity Ford ø 8 at 20°C ±2</b>	120-125
<b>Shelf life (+10+30°C)</b>	18 months in airtight cans

#### Application Data

<b>Brush-Roller</b>	Brush to touch up 10-15% Thinner 400
<b>Spray</b>	normal colors spray 20-30% Thinner 400 - Spray metall colors. 30-40% Thinner 765
<b>Touch dry</b>	2-4 h (20°C)
<b>Application temperature</b>	Between +10 C et +40 C
<b>Relevant humidity</b>	Less than 80%
<b>Dry film thickness advised</b>	40 microns by hand
<b>Theoret. coverage m2/Lt</b>	10-12

### SURFACE PREPARATION AND RECOMMENDED COATING SYSTEM

#### Bare steel new surfaces

. Degrease the substrate and apply one primer coat of EPOFOND AM-9 by spray or by brush. Let dry for 12-24 hours and apply one coat of SOLVER PRIMER by spray or by brush. Let dry for 12-24 hours and overcoat with 1-2 coats of SMALTO MOTORI MARINI in the desired shade as per colours available.

#### Painted surfaces.

Remove all loose parts by wirebrushing or by means of paint remover or by sanding. Degrease the surface and sandpaper the existing paint. Apply 1 or 2 coats of SOLVER PRIMER all over the surface (both on old paint and over parts brought back to bare steel). Let dry for 12-4 hours and apply 1-2 coats of SMALTO MOTORI MARINI in the desired shade as per colours available.

In case it is only required to refresh the old finish just because dirty or dull but still with good adhesion properties and free from cracking or loose parts, sandpaper and apply directly 1-2 coats of SMALTO MOTORI MARINI in the desired shade as per colours available.

Codice: MMO

# Smalto Motori Marini

NB: This product is part of the Skipper's Line of Marine Coatings. For further application details please also see the "Indicative Coating Systems information" available on demand for Wood, Steel, Aluminium and Fibreglass boats. When in doubt contact for advise.


## Colors



Colore: AVORIO ONAN  
Cod. Colore: MM0085



Colore: AZZURRO PERKINS  
Cod. Colore: MM0120



Colore: BIANCO  
Cod. Colore: MM0080




Colore: BLU AIFO  
Cod. Colore: MM0121



Colore: BLU METALL. NANNI  
Cod. Colore: MM0124



Colore: BLU OMC  
Cod. Colore: MM0123



Colore: BLU VM  
Cod. Colore: MM0122



Colore: BMW SILVER  
Cod. Colore: MM0132



Colore: GIALLO CATERPILLAR  
Cod. Colore: MM0011



Colore: GIALLO VETUS  
Cod. Colore: MM0110



Colore: GRIGIO MET YANM  
Cod. Colore: MM0130



Colore: GRIGIO VOLVO  
Cod. Colore: MM0131



Colore: NERO MERCURY  
Cod. Colore: MM0070



Colore: NERO VOLVO  
Cod. Colore: MM0710



Colore: ROSSO AIFO  
Cod. Colore: MM0150



Colore: ROSSO VOLVO  
Cod. Colore: MM0151



Colore: VERDE GM  
Cod. Colore: MM0175



Colore: VERDE VOLVO  
Cod. Colore: MM0174

## Listino

Formati Disponibili	Codice	Descrizione	Confezione
0.75L	MM007000750	Smalto motori marini nero Mercury	0.75 lt
	MM007100750	Smalto motori marini nero Volvo	0.75 lt
	MM008000750	Smalto motori marini bianco cummins	0.75 lt

Codice	Descrizione	Confezione
MM008500750	Smalto motori marini bianco onan ivory	0.75 lt
MM011000750	Smalto motori marini giallo vetus 40.094	0.75 lt
MM011100750	Smalto motori marini giallo caterpillar	0.75 lt
MM012000750	Smalto motori marini azzurro perkins	0.75 lt
MM012100750	Smalto motori marini blu aifo	0.75 lt
MM012200750	Smalto motori marini blu VM	0.75 lt
MM012300750	Smalto motori marini blu O.M.C. 097	0.75 lt
MM012400750	Smalto motori marini nanni blu met.40095	0.75 lt
MM013000750	Smalto motori marini yanmar grigio met.0083	0.75 lt
MM013100750	Smalto motori marini grigio volvo 086	0.75 lt
MM013200750	Smalto motori marini bmw silver 0089	0.75 lt
MM015000750	Smalto motori marini rosso aifo 310	0.75 lt
MM015100750	Smalto motori marini rosso Volvo	0.75 lt
MM017400750	Smalto motori marini verde penta volvo 340	0.75 lt
MM017500750	Smalto motori marini verde GM 087	0.75 lt

**SAFETY PRECAUTIONS**

Before starting paint application attention should be paid to the symbols of risk specified on the label of each can. Please carefully read all the safety precautions advised on the label, or in the safety data sheet available on request at [laboratorio@aemmecolori.it](mailto:laboratorio@aemmecolori.it)

**NOTES**

This information is provided to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, this information does not constitute any kind of implied warranties; in that sense the supplying company accepts from now responsibility that can be connected to an abnormal use of the products. The Engineering Department at your location is available for any questions related to the use of our products. The percentages of dilution and the drying time are to be considered only indicative, in relation to a temperature of 20 ° C and are therefore subject to change with the change of temperature, in the presence of particular weather conditions or application determining factors at the time of 'application.